

Polymer	Characteristics	Application	Quality	Product Number
polyamide 66	PA66 reinforced with glass fibre, heat stabilised, hydrolysis resistant	injection moulding	prime	1333000

Properties (in natural colour at 23°C)	Unit	Test Method	Value
<b>General</b>			
Symbols and abbreviated terms		STN EN ISO 1043-1	PA 66
Density	g/cm <sup>3</sup>	STN EN ISO 1183-1	1,29
Type of the filler: GF, GB, MF, G			GF
Stabilisation: TS, LS, K			TS
Modification: FR, HI, MI, ME			
Colour: NA, F, BK			NA/BK
<b>Processing</b>			
Processing method: IM, E	°C		IM
Melting point DSC	°C	STN EN ISO 11357-1	262
Melt temperature range	°C		250 - 290
Mould temperature range	°C		80 - 120
Injection pressure	MPa		80 - 110
Drying: temperature/time	°C/H		90/4
Water content	%	STN EN ISO 3344	0,15
Melt flow rate 275°C/2,16 kg	g/10 min	STN EN ISO 1133	10
Manufacturing shrinkage length / width	%	STN EN ISO 294-4	0,6/0,8
<b>Mechanical</b>			
Tensile strength	MPa	STN EN ISO 527-2	125
Elongation	%	STN EN ISO 527-2	3,5
Tensile modulus	MPa	STN EN ISO 527-2	5500
Flexural modulus	MPa	STN EN ISO 178	4700
Flexural strength	MPa	STN EN ISO 178	205
Charpy impact strength 23°C	kJ/m <sup>2</sup>	STN EN ISO 179	40
Charpy impact strength -20°C	kJ/m <sup>2</sup>	STN EN ISO 179	35
Charpy notched impact strength 23°C	kJ/m <sup>2</sup>	STN EN ISO 179	5
Charpy notched impact strength -20°C	kJ/m <sup>2</sup>	STN EN ISO 179	3
<b>Thermal</b>			
Heat deflection temperature	°C	STN EN ISO 75-2 (A)	250
Vicat softening point B	°C	STN EN ISO 306	250
<b>Flammability</b>			
Flammability	°flam.	UL - 94	HB
Glow wire test	°C	STN EN 60695-2-12	650 (3mm)

Electrical			
Comparative tracking index CTI, A	V	STN EN 60112	
Volume resistivity	Ohm.m	STN 34 6460	
Surface resistivity	Ohm	STN 34 6460	
Electric strength	kV/mm	STN EN 60243-2	

### Features

PA66 for injection moulding, reinforced with 20% glass fibre, heat stabilised, hydrolysis resistant, for mouldings used in the automotive, electrical, building, engineering and hobby industry - holders of electric hand tools, hobby tools, gears, covers of electric tools, automobile mirror housings, cooling screws of blowers, electromotors, bearing parts in the automotive industry. Delivered in black color and in natural form.

### Packaging, transportation, storage

The product is packed either in hermetically closed thick-walled 25 kg PE bags placed on a 1.000 kg palette coated by a stretch film, or in PE bag inserted in bigbag placed on a 1.000 kg palette or in PE bag inserted in paper octabin placed on a 1.000 kg palette or in other packaging according to customer requirements. The transport is provided in closed-up vehicles where the material is protected against movement and mechanical damage. The product requires stocking in closed-up, dry places protected against sun and thermal radiation.

### NOTE:

Data and values are average measured values, they are intended for technical service advices and can be changed without prior notice.

Contact: Sales Department;  
Tel: +421 2 44 259160; fax: +421 2 44259223; E-mail: [office@plastcom.sk](mailto:office@plastcom.sk); Url: [www.plastcom.sk](http://www.plastcom.sk)