

Polymer	Characteristics	Application	Quality	Product Number
polyamide 66	PA66 flame retarded, heat stabilised	injection moulding	prime	1347000

Properties (in natural colour at 23°C)	Unit	Test Method	Value
General			
Symbols and abbreviated terms		STN EN ISO 1043-1	PA 66
Density	g/cm ³	STN EN ISO 1183-1	1.17
Type of the filler: GF, GB, MF, G			
Stabilisation: TS, LS, K			TS
Modification: FR, HI, MI, ME			FR
Colour: NA, F, BK			NA/F
Processing			
Processing method: IM, E	°C		IM
Melting point DSC	°C	STN EN ISO 11357-1	255
Melt temperature range	°C		250 - 270
Mould temperature range	°C		50 - 70
Injection pressure	MPa		70 - 90
Drying: temperature/time	°C/H		80/4
Water content	%	STN EN ISO 3344	0,1
Melt flow rate 275°C/0,325 kg	g/10 min	STN EN ISO 1133	5
Manufacturing shrinkage length / width	%	STN EN ISO 294-4	1,2/1,4
Mechanical			
Tensile strength	MPa	STN EN ISO 527-2	85
Elongation	%	STN EN ISO 527-2	4
Tensile modulus	MPa	STN EN ISO 527-2	3700
Flexural modulus	MPa	STN EN ISO 178	3500
Flexural strength	MPa	STN EN ISO 178	145
Charpy impact strength 23°C	kJ/m ²	STN EN ISO 179	NB
Charpy impact strength -20°C	kJ/m ²	STN EN ISO 179	85
Charpy notched impact strength 23°C	kJ/m ²	STN EN ISO 179	3
Charpy notched impact strength -20°C	kJ/m ²	STN EN ISO 179	2
Thermal			
Heat deflection temperature	°C	STN EN ISO 75-2 (A)	75
Vicat softening point B	°C	STN EN ISO 306	235
Flammability			
Flammability	°flam.	UL - 94	V 0 (1,6mm)
Glow wire test	°C	STN EN 60695-2-12	960 (3mm)

Electrical			
Comparative tracking index CTI, A	V	STN EN 60112	650
Volume resistivity	Ohm.m	STN 34 6460	1x10 ¹³
Surface resistivity	Ohm	STN 34 6460	1x10 ¹⁴
Electric strength	kV/mm	STN EN 60243-2	25

Features

PA66 modified for general use, flame retarded, heat stabilised. Used in automotive, electrical, engineering and consumer goods industry. Application: electric tools, gear wheels, clamps, fasteners, toolbodies, webbing slings for cable harnesses. Possible use for products with wall thickness from 0.8 mm (V0 according to 0,8mm). High grade brightness also at coloured types. Delivered in the full RAL colour scale.

Packaging, transportation, storage

The product is packed either in hermetically closed thick-walled 25 kg PE bags placed on a 1.000 kg palette coated by a stretch film, or in PE bag inserted in bigbag placed on a 1.000 kg palette or in PE bag inserted in paper octabin placed on a 1.000 kg palette or in other packaging according to customer requirements. The transport is provided in closed-up vehicles where the material is protected against movement and mechanical damage. The product requires stocking in closed-up, dry places protected against sun and thermal radiation.

NOTE:

Data and values are average measured values, they are intended for technical service advices and can be changed without prior notice.

Contact: Sales Department;
Tel: +421 2 44 259160; fax: +421 2 44259223; E-mail: office@plastcom.sk; Url: www.plastcom.sk