

| Polymer | Characteristics | Application | Quality | Product Number |
|-------------|--|--------------------|---------|----------------|
| polyamide 6 | PA6 flame retarded, impact modified | injection moulding | prime | 198000 |

| Properties (in natural colour at 23°C) | Unit | Test Method | Value |
|--|-------------------|---------------------|-------------|
| General | | | |
| Symbols and abbreviated terms | | STN EN ISO 1043-1 | PA 6 |
| Density | g/cm ³ | STN EN ISO 1183-1 | 1,16 |
| Type of the filler: GF, GB, MF, G | | | |
| Stabilisation: TS, LS, K | | | |
| Modification: FR, HI, MI, ME | | | FR, LI |
| Colour: NA, F, BK | | | NA/F |
| Processing | | | |
| Processing method: IM, E | °C | | IM |
| Melting point DSC | °C | STN EN ISO 11357-1 | 220 |
| Melt temperature range | °C | | 250-270 |
| Mould temperature range | °C | | 50-70 |
| Injection pressure | MPa | | 70-100 |
| Drying: temperature/time | °C/H | | 80/4 |
| Water content | % | STN EN ISO 3344 | 0,15 |
| Melt flow rate 230°C/2,16 kg | g/10 min | STN EN ISO 1133 | 10 |
| Manufacturing shrinkage length / width | % | STN EN ISO 294-4 | 1,53/1,21 |
| Mechanical | | | |
| Tensile strength | MPa | STN EN ISO 527-2 | 70 |
| Elongation | % | STN EN ISO 527-2 | 4 |
| Tensile modulus | MPa | STN EN ISO 527-2 | 2500 |
| Flexural modulus | MPa | STN EN ISO 178 | 2300 |
| Flexural strength | MPa | STN EN ISO 178 | 90 |
| Charpy impact strength 23°C | kJ/m ² | STN EN ISO 179 | 120 |
| Charpy impact strength -20°C | kJ/m ² | STN EN ISO 179 | 110 |
| Charpy notched impact strength 23°C | kJ/m ² | STN EN ISO 179 | 7 |
| Charpy notched impact strength -20°C | kJ/m ² | STN EN ISO 179 | 3 |
| Thermal | | | |
| Heat deflection temperature | °C | STN EN ISO 75-2 (A) | 60 |
| Vicat softening point B | °C | STN EN ISO 306 | 200 |
| Flammability | | | |
| Flammability | °flam. | UL - 94 | V 2 (1,6mm) |
| Glow wire test | °C | STN EN 60695-2-12 | 960 (3mm) |

| Electrical | | | |
|-----------------------------------|-------|----------------|--|
| Comparative tracking index CTI, A | V | STN EN 60112 | |
| Volume resistivity | Ohm.m | STN 34 6460 | |
| Surface resistivity | Ohm | STN 34 6460 | |
| Electric strength | kV/mm | STN EN 60243-2 | |
| | | | |

Features

PA 6 for injection moulding flame retarded with nonhalogen flame retardant, impact modified. Determined for electrotechnical use. Excellent fluidity of the material predetermines it for the manufacturing of complicated small and large surface mouldings. High grade brightness also at coloured types. Delivered in natural as well as the full RAL colour scale.

Packaging, transportation, storage

The product is packed either in hermetically closed thick-walled 25 kg PE bags placed on a 1.000 kg palette coated by a stretch film, or in PE bag inserted in bigbag placed on a 1.000 kg palette or in PE bag inserted in paper octabin placed on a 1.000 kg palette or in other packaging according to customer requirements. The transport is provided in closed-up vehicles where the material is protected against movement and mechanical damage. The product requires stocking in closed-up, dry places protected against sun and thermal radiation.

NOTE:

Data and values are average measured values, they are intended for technical service advices and can be changed without prior notice.

Contact: Sales Department;

Tel: +421 2 44 259160; fax: +421 2 44259223; E-mail: office@plastcom.sk; Url: www.plastcom.sk

Centrála:

Plastcom, spol. s r.o.
Hattalova 4, 831 03 Bratislava
Tel: 00421 2 44 259 160
Fax: 00421 2 44 259 223

Závod:

Plastcom, spol. s r.o.
Štúrova 53, 949 01 Nitra
Tel: 00421 37 77 29 419
Fax: 00421 37 77 29 418

Spoločnosť je zapísaná
v Obchodnom registri Okresného súdu
Bratislava I.,
oddiel Sro, Vložka číslo: 903/B