

Polymer	Characteristics	Application	Quality	Product Number
polypropylene	PP reinforced with mineral filler, detergent resistant	injection moulding	prime	276000

Properties (in natural colour at 23°C)	Unit	Test Method	Value
General			
Symbols and abbreviated terms		STN EN ISO 1043-1	PP
Density	g/cm ³	STN EN ISO 1183-1	1,23
Type of the filler: GF, GB, MF, G			MF
Stabilisation: TS, LS, K			K
Modification: FR, HI, MI, ME			
Colour: NA, F, BK			NA/F
Processing			
Processing method: IM, E	°C		IM
Melting point DSC	°C	STN EN ISO 11357-1	160
Melt temperature range	°C		200-250
Mould temperature range	°C		40-70
Injection pressure	MPa		70-120
Drying: temperature/time	°C/H		70/4
Water content	%	STN EN ISO 3344	
Melt flow rate 230°C/2,16 kg	g/10 min	STN EN ISO 1133	10
Manufacturing shrinkage length / width	%	STN EN ISO 294-4	1,44/1,65
Mechanical			
Tensile strength	MPa	STN EN ISO 527-2	34
Elongation	%	STN EN ISO 527-2	4,1
Tensile modulus	MPa	STN EN ISO 527-2	3600
Flexural modulus	MPa	STN EN ISO 178	3700
Flexural strength	MPa	STN EN ISO 178	47
Charpy impact strength 23°C	kJ/m ²	STN EN ISO 179	43
Charpy impact strength -20°C	kJ/m ²	STN EN ISO 179	23
Charpy notched impact strength 23°C	kJ/m ²	STN EN ISO 179	4,6
Charpy notched impact strength -20°C	kJ/m ²	STN EN ISO 179	1
Thermal			
Heat deflection temperature	°C	STN EN ISO 75-2 (A)	130
Vicat softening point B	°C	STN EN ISO 306	160
Flammability			
Flammability	°flam.	UL - 94	
Glow wire test	°C	STN EN 60695-2-12	

Electrical			
Comparative tracking index CTI, A	V	STN EN 60112	
Volume resistivity	Ohm.m	STN 34 6460	
Surface resistivity	Ohm	STN 34 6460	
Electric strength	kV/mm	STN EN 60243-2	

Features

Modified homopolymer PP for injection moulding with the content of 40% mineral filler, detergents resistant. General application in all industry branches. Delivered in natural mode and in the full RAL colour scale.

Packaging, transportation, storage

The product is packed either in hermetically closed thick-walled 25 kg PE bags placed on a 1.000 kg palette coated by a stretch film, or in PE bag inserted in bigbag placed on a 1.000 kg palette or in PE bag inserted in paper octabin placed on a 1.000 kg palette or in other packaging according to customer requirements. The transport is provided in closed-up vehicles where the material is protected against movement and mechanical damage. The product requires stocking in closed-up, dry places protected against sun and thermal radiation.

NOTE:

Data and values are average measured values, they are intended for technical service advices and can be changed without prior notice.

Contact: Sales Department;

Tel: +421 2 44 259160; fax: +421 2 44259223; E-mail: office@plastcom.sk; Url: www.plastcom.sk

Centrála:

Plastcom, spol. s r.o.
Hattalova 4, 831 03 Bratislava
Tel: 00421 2 44 259 160
Fax: 00421 2 44 259 223

Závod:

Plastcom, spol. s r.o.
Štúrova 53, 949 01 Nitra
Tel: 00421 37 77 29 419
Fax: 00421 37 77 29 418

Spoločnosť je zapísaná
v Obchodnom registri Okresného súdu
Bratislava I.,
oddiel Sro, Vložka číslo: 903/B