

Polymer	Characteristics	Application	Quality	Product Number
polyamide 66	PA66 reinforced with glass fibre, heat stabilised, hydrolysis resistant	injection moulding	prime	1343000

Properties (in natural colour at 23°C)	Unit	Test Method	Value
<b>General</b>			
Symbols and abbreviated terms		STN EN ISO 1043-1	PA 66
Density	g/cm <sup>3</sup>	STN EN ISO 1183-1	1,49
Type of the filler: GF, GB, MF, G			GF
Stabilisation: TS, LS, K			HTS
Modification: FR, HI, MI, ME			
Colour: NA, F, BK			NA/F
<b>Processing</b>			
Processing method: IM, E	°C		IM
Melting point DSC	°C	STN EN ISO 11357-1	260
Melt temperature range	°C		260 - 300
Mould temperature range	°C		70 - 100
Injection pressure	MPa		70 - 120
Drying: temperature/time	°C/H		80/4
Water content	%	STN EN ISO 3344	0,15
Melt flow rate 275°C/2,16 kg	g/10 min	STN EN ISO 1133	5
Manufacturing shrinkage length / width	%	STN EN ISO 294-4	0,7/0,9
<b>Mechanical</b>			
Tensile strength	MPa	STN EN ISO 527-2	210
Elongation	%	STN EN ISO 527-2	2
Tensile modulus	MPa	STN EN ISO 527-2	14800
Flexural modulus	MPa	STN EN ISO 178	11250
Flexural strength	MPa	STN EN ISO 178	265
Charpy impact strength 23°C	kJ/m <sup>2</sup>	STN EN ISO 179	95
Charpy impact strength -20°C	kJ/m <sup>2</sup>	STN EN ISO 179	90
Charpy notched impact strength 23°C	kJ/m <sup>2</sup>	STN EN ISO 179	14
Charpy notched impact strength -20°C	kJ/m <sup>2</sup>	STN EN ISO 179	12
<b>Thermal</b>			
Heat deflection temperature	°C	STN EN ISO 75-2 (A)	255
Vicat softening point B	°C	STN EN ISO 306	250
<b>Flammability</b>			
Flammability	°flam.	UL - 94	HB
Glow wire test	°C	STN EN 60695-2-12	650 (3mm)

Electrical			
Comparative tracking index CTI, A	V	STN EN 60112	
Volume resistivity	Ohm.m	STN 34 6460	1x10 <sup>13</sup>
Surface resistivity	Ohm	STN 34 6460	1x10 <sup>14</sup>
Electric strength	kV/mm	STN EN 60243-2	25

### Features

PA66 for injection moulding grade, reinforced with 45% glass fibre, heat stabilised, hydrolysis resistant, determined for injection moulding of parts like oil pipes, parts in engine. Delivered in natural and black color.

### Packaging, transportation, storage

The product is packed either in hermetically closed thick-walled 25 kg PE bags placed on a 1.000 kg palette coated by a stretch film, or in PE bag inserted in bigbag placed on a 1.000 kg palette or in PE bag inserted in paper octabin placed on a 1.000 kg palette or in other packaging according to customer requirements. The transport is provided in closed-up vehicles where the material is protected against movement and mechanical damage. The product requires stocking in closed-up, dry places protected against sun and thermal radiation.

### NOTE:

Data and values are average measured values, they are intended for technical service advices and can be changed without prior notice.

Contact: Sales Department;

Tel: +421 2 44 259160; fax: +421 2 44259223; E-mail: [office@plastcom.sk](mailto:office@plastcom.sk); Url: [www.plastcom.sk](http://www.plastcom.sk)

#### Centrála:

Plastcom, spol. s r.o.  
Hattalova 4, 831 03 Bratislava  
Tel: 00421 2 44 259 160  
Fax: 00421 2 44 259 223

#### Závod:

Plastcom, spol. s r.o.  
Štúrova 53, 949 01 Nitra  
Tel: 00421 37 77 29 419  
Fax: 00421 37 77 29 418

Spoločnosť je zapísaná  
v Obchodnom registri Okresného súdu  
Bratislava I.,  
oddiel Sro, Vložka číslo: 903/B