

Polymer	Characteristics	Application	Quality	Product Number
polyamide 6/66C	PA6/66 copolymer reinforced with mineral, improved impact strength	injection moulding	prime	1518000

Properties (in natural colour at 23°C)	Unit	Test Method	Value
<b>General</b>			
Symbols and abbreviated terms		STN EN ISO 1043-1	PA 6/66C
Density	g/cm <sup>3</sup>	STN EN ISO 1183-1	1,2
Type of the filler: GF, GB, MF, G			MF
Stabilisation: TS, LS, K			
Modification: FR, HI, MI, ME			HI
Colour: NA, F, BK			NA/F
<b>Processing</b>			
Processing method: IM, E	°C		IM
Melting point DSC	°C	STN EN ISO 11357-1	200
Melt temperature range	°C		250-270
Mould temperature range	°C		70-90
Injection pressure	MPa		70-120
Drying: temperature/time	°C/H		80/4
Water content	%	STN EN ISO 3344	0,15
Melt flow rate 275°C/2,16 kg	g/10 min	STN EN ISO 1133	30
Manufacturing shrinkage length / width	%	STN EN ISO 294-4	0,85/0,9
<b>Mechanical</b>			
Tensile strength	MPa	STN EN ISO 527-2	55
Elongation	%	STN EN ISO 527-2	3,5
Tensile modulus	MPa	STN EN ISO 527-2	3600
Flexural modulus	MPa	STN EN ISO 178	2400
Flexural strength	MPa	STN EN ISO 178	70
Charpy impact strength 23°C	kJ/m <sup>2</sup>	STN EN ISO 179	0
Charpy impact strength -20°C	kJ/m <sup>2</sup>	STN EN ISO 179	0
Charpy notched impact strength 23°C	kJ/m <sup>2</sup>	STN EN ISO 179	13
Charpy notched impact strength -20°C	kJ/m <sup>2</sup>	STN EN ISO 179	10
<b>Thermal</b>			
Heat deflection temperature	°C	STN EN ISO 75-2 (A)	180
Vicat softening point B	°C	STN EN ISO 306	225
<b>Flammability</b>			
Flammability	°flam.	UL - 94	HB
Glow wire test	°C	STN EN 60695-2-12	650 (3mm)

Electrical			
Comparative tracking index CTI, A	V	STN EN 60112	400
Volume resistivity	Ohm.m	STN 34 6460	1x10 <sup>13</sup>
Surface resistivity	Ohm	STN 34 6460	1x10 <sup>15</sup>
Electric strength	kV/mm	STN EN 60243-2	25

### Features

PA 6/66 copolymer for injection moulding, reinforced with 20% mineral filler and with the content of thermoplastic elastomer. Application: impacted mouldings and mouldings with high impact applied in automotive, electrical, engineering and consumergoods industry, eg.: grips for electro tools, hobby tools, gears, cases of the electrottools, cooling screws of blowers, electromotors, carrying parts in the automotive industry. Delivered in natural mode and in the full RAL colour scale.

### Packaging, transportation, storage

The product is packed either in hermetically closed thick-walled 25 kg PE bags placed on a 1.000 kg palette coated by a stretch film, or in PE bag inserted in bigbag placed on a 1.000 kg palette or in PE bag inserted in paper octabin placed on a 1.000 kg palette or in other packaging according to customer requirements. The transport is provided in closed-up vehicles where the material is protected against movement and mechanical damage. The product requires stocking in closed-up, dry places protected against sun and thermal radiation.

### NOTE:

Data and values are average measured values, they are intended for technical service advices and can be changed without prior notice.

Contact: Sales Department;  
Tel: +421 2 44 259160; fax: +421 2 44259223; E-mail: [office@plastcom.sk](mailto:office@plastcom.sk); Url: [www.plastcom.sk](http://www.plastcom.sk)