

Polymer	Characteristics	Application	Quality	Product Number
polyamide 6	PA6 reinforced with glass fibre, heat stabilised	injection moulding	prime	916000

Properties (in natural colour at 23°C)	Unit	Test Method	Value
<b>General</b>			
Symbols and abbreviated terms		STN EN ISO 1043-1	PA 6
Density	g/cm <sup>3</sup>	STN EN ISO 1183-1	1,34
Type of the filler: GF, GB, MF, G			GF
Stabilisation: TS, LS, K			TS
Modification: FR, HI, MI, ME			
Colour: NA, F, BK			NA/F
<b>Processing</b>			
Processing method: IM, E	°C		IM
Melting point DSC	°C	STN EN ISO 11357-1	220
Melt temperature range	°C		250-270
Mould temperature range	°C		70-90
Injection pressure	MPa		70-120
Drying: temperature/time	°C/H		80/4
Water content	%	STN EN ISO 3344	0,15
Melt flow rate 230°C/2,16 kg	g/10 min	STN EN ISO 1133	3
Manufacturing shrinkage length / width	%	STN EN ISO 294-4	0,85/1,45
<b>Mechanical</b>			
Tensile strength	MPa	STN EN ISO 527-2	180
Elongation	%	STN EN ISO 527-2	4
Tensile modulus	MPa	STN EN ISO 527-2	10000
Flexural modulus	MPa	STN EN ISO 178	7500
Flexural strength	MPa	STN EN ISO 178	230
Charpy impact strength 23°C	kJ/m <sup>2</sup>	STN EN ISO 179	90
Charpy impact strength -20°C	kJ/m <sup>2</sup>	STN EN ISO 179	75
Charpy notched impact strength 23°C	kJ/m <sup>2</sup>	STN EN ISO 179	15
Charpy notched impact strength -20°C	kJ/m <sup>2</sup>	STN EN ISO 179	13
<b>Thermal</b>			
Heat deflection temperature	°C	STN EN ISO 75-2 (A)	205
Vicat softening point B	°C	STN EN ISO 306	210
<b>Flammability</b>			
Flammability	°flam.	UL - 94	HB
Glow wire test	°C	STN EN 60695-2-12	650 (3mm)

Electrical			
Comparative tracking index CTI, A	V	STN EN 60112	
Volume resistivity	Ohm.m	STN 34 6460	
Surface resistivity	Ohm	STN 34 6460	
Electric strength	kV/mm	STN EN 60243-2	

### Features

PA 6 for injection moulding new generation, reinforced with 30% glass fibre, heat stabilised. Application: impacted mouldings applied in automotive, electrical, engineering and consumer-goods industry, eg.: grips for electro tools, hobby tools, gears, cases of the electrotols, cooling screws of blowers, electromotors, carrying parts in the automotive industry.  
Delivered in natural as well as mode full RAL colour scale.

### Packaging, transportation, storage

The product is packed either in hermetically closed thick-walled 25 kg PE bags placed on a 1.000 kg palette coated by a stretch film, or in PE bag inserted in bigbag placed on a 1.000 kg palette or in PE bag inserted in paper octabin placed on a 1.000 kg palette or in other packaging according to customer requirements. The transport is provided in closed-up vehicles where the material is protected against movement and mechanical damage. The product requires stocking in closed-up, dry places protected against sun and thermal radiation.

### NOTE:

Data and values are average measured values, they are intended for technical service advices and can be changed without prior notice.

Contact: Sales Department;  
Tel: +421 2 44 259160; fax: +421 2 44259223; E-mail: [office@plastcom.sk](mailto:office@plastcom.sk); Url: [www.plastcom.sk](http://www.plastcom.sk)