

Polymer	Characteristics	Application	Quality	Product Number
polyamide 6/66	PA6/66 reinforced with glass fibre, flame retarded, heat stabilised	injection moulding	prime	969000

Properties (in natural colour at 23°C)	Unit	Test Method	Value
General			
Symbols and abbreviated terms		STN EN ISO 1043-1	PA 6/66
Density	g/cm ³	STN EN ISO 1183-1	1,4
Type of the filler: GF, GB, MF, G			GF
Stabilisation: TS, LS, K			TS
Modification: FR, HI, MI, ME			FR
Colour: NA, F, BK			NA/F
Processing			
Processing method: IM, E	°C		IM
Melting point DSC	°C	STN EN ISO 11357-1	262
Melt temperature range	°C		270-300
Mould temperature range	°C		70-100
Injection pressure	MPa		70-100
Drying: temperature/time	°C/H		80/4
Water content	%	STN EN ISO 3344	0,15
Melt flow rate 230°C/2,16 kg	g/10 min	STN EN ISO 1133	2
Manufacturing shrinkage length / width	%	STN EN ISO 294-4	0,4/0,52
Mechanical			
Tensile strength	MPa	STN EN ISO 527-2	195
Elongation	%	STN EN ISO 527-2	2
Tensile modulus	MPa	STN EN ISO 527-2	10000
Flexural modulus	MPa	STN EN ISO 178	8750
Flexural strength	MPa	STN EN ISO 178	245
Charpy impact strength 23°C	kJ/m ²	STN EN ISO 179	85
Charpy impact strength -20°C	kJ/m ²	STN EN ISO 179	75
Charpy notched impact strength 23°C	kJ/m ²	STN EN ISO 179	11
Charpy notched impact strength -20°C	kJ/m ²	STN EN ISO 179	8
Thermal			
Heat deflection temperature	°C	STN EN ISO 75-2 (A)	245
Vicat softening point B	°C	STN EN ISO 306	252
Flammability			
Flammability	°flam.	UL - 94	V 0 (0,8mm)
Glow wire test	°C	STN EN 60695-2-12	960 (3mm)

Electrical			
Comparative tracking index CTI, A	V	STN EN 60112	650
Volume resistivity	Ohm.m	STN 34 6460	1x10 ¹³
Surface resistivity	Ohm	STN 34 6460	1x10 ¹⁵
Electric strength	kV/mm	STN EN 60243-2	60

Features

PA 6 + PA 66 alloy reinforced with 30% GF for injection moulding flame retarded with nonhalogen flame retardant, heat stabilised. Determined for electrotechnical use. Excellent flow of the material predetermines it for the manufacturing of complicated small and large surface mouldings. High grade brightness also at coloured types.
Delivered in natural as well as in full RAL colour scale.

Packaging, transportation, storage

The product is packed either in hermetically closed thick-walled 25 kg PE bags placed on a 1.000 kg palette coated by a stretch film, or in PE bag inserted in bigbag placed on a 1.000 kg palette or in PE bag inserted in paper octabin placed on a 1.000 kg palette or in other packaging according to customer requirements. The transport is provided in closed-up vehicles where the material is protected against movement and mechanical damage. The product requires stocking in closed-up, dry places protected against sun and thermal radiation.

NOTE:

Data and values are average measured values, they are intended for technical service advices and can be changed without prior notice.

Contact: Sales Department;
Tel: +421 2 44 259160; fax: +421 2 44259223; E-mail: office@plastcom.sk; Url: www.plastcom.sk